

AMENDMENTS TO THE SPECIFICATION

IN THE SPECIFICATION:

Please replace page 25 with the following amended page 25 as follows:

Table 1

		Example 1	Example 2	<u>Comparative</u> <u>Example 3 1</u>
Composition (parts)	Liquid crystal Polyester	100	100	100
	Glass balloon	18.8	18.8	18.8
	Glass fiber	6.3	6.3	6.3
Supplying position	Liquid crystal polyester	upper stream side	upper stream side	upper stream side
	Glass balloon	lower stream side	lower stream side	lower stream side
	Glass fiber	upper stream side	lower stream side	upper stream side
L/D	L/D	14	14	-
Evaluation	Specific gravity	1.21	1.24	1.35
	Breakdown Rate%	12.1	22.6	57.2
	Heat Conductivity W/mK	0.39	0.41	0.45
	Bending Strength (kg/cm ²)	910	1050	1170

According to the process of the present invention, a hollow spheres-containing thermoplastic resin composition of low specific gravity can be manufactured by a melt processing extrusion method.